

Appln. No. 10/821,170
Reply to Office action of September 19, 2005
Response dated February 21, 2006

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (Currently Amended) A Co-Cr-Mo alloy fine wire, ~~comprising~~ consisting of: 26 to 31 weight % of Cr; more than 8 weight % 8 to 16 weight % of Mo; and the remainder of Co and inevitable impurities; the wire having a diameter of 200 micrometers or less and a degree of roundness (minor diameter/major diameter) of lateral cross section of 0.6 or more, and a uniform structure with a concentration ratio of a high Mo concentration phase with respect to a low Mo concentration phase of 1.8 or less.

Claim 2 (Original) The Co-Cr-Mo alloy fine wire of claim 1, wherein the structure is uniform with the concentration ratio of high Co concentration phase to low Co concentration phase of 1.1 or less.

Claim 3 (Original) The Co-Cr-Mo alloy fine wire of claim 1, wherein the structure is uniform with the concentration ratio of high Cr concentration phase to low Cr concentration phase of 1.1 or less.

Claim 4 (Original) The Co-Cr-Mo alloy fine wire of claim 1, wherein the roundness of lateral cross section is 0.7 or more.

Claim 5 (Original) A manufacturing method for Co-Cr-Mo alloy fine wire, the method comprising the steps of:

injecting a molten alloy comprising 26 to 31 weight % of Cr, 8 to 16 weight % of Mo, and the remainder of Co and inevitable impurities from a nozzle with an inner diameter of 200 micrometers or less to form a molten alloy jet; and

solidifying the molten alloy jet in a coolant layer formed along an inner circumference of a rotating cylindrical drum.

Appln. No. 10/821,170
Reply to Office action of September 19, 2005
Response dated February 21, 2006

Claim 6 (Original) A manufacturing method for Co-Cr-Mo alloy fine wire, the method comprising the steps of:

injecting a molten alloy comprising 26 to 31 weight % of Cr, 8 to 16 weight % of Mo, and the remainder of Co and inevitable impurities from a nozzle of 200 micrometers or less in diameter to form a molten alloy jet; and

cooling and solidifying the molten alloy jet in cooling gas.

Claim 7 (Original) A manufacturing method for Co-Cr-Mo alloy fine wire, the method comprising the steps of:

injecting a molten alloy comprising 26 to 31 weight % of Cr, 8 to 16 weight % of Mo, and the remainder of Co and inevitable impurities from a nozzle of 200 micrometers or less in diameter to form a molten alloy jet;

feeding cooling gas into a tube collecting gas disposed in a manner so as to surround the falling path of the molten alloy jet to solidify the molten alloy jet; and

discharging the fine wire from the discharge part of the tube collecting gas to outside.

Claim 8 (Original) The manufacturing method for Co-Cr-Mo alloy fine wire of claim 6, wherein the cooling gas is a gas containing oxygen.

Claim 9 (Original) The manufacturing method for Co-Cr-Mo alloy fine wire of claim 6, wherein the cooling gas is composed of a first gas component comprising inert gas introduced into the tube collecting gas at a first position closer to the nozzle in the falling direction of the molten alloy jet, and a second gas component comprising oxidizing gas introduced into the tube collecting gas at a second position at lower side of the first position.

Claim 10 (Original) The manufacturing method for Co-Cr-Mo alloy fine wire of claim 9, wherein the first gas component is argon or helium, and the second gas component is oxygen or carbon dioxide.

TECH/400118.1

Appln. No. 10/821,170
Reply to Office action of September 19, 2005
Response dated February 21, 2006

Claim 11 (Original) A planar body formed by weaving, knitting or nonwoven processing of the Co-Cr-Mo alloy fine wire of claim 1.

Claim 12 (Original) A tubular body formed by weaving, knitting or nonwoven processing of the Co-Cr-Mo alloy fine wire of claim 1.

Claim 13 (Original) A stranded wire formed by processing of the Co-Cr-Mo alloy fine wire of claim 1.

Claim 14 (Original) A cable formed by processing of the Co-Cr-Mo alloy fine wire of claim 1.

Claim 15 (Currently Amended) A Co-Cr-Mo alloy fine wire, ~~comprising~~ consisting of 26 to 31 weight % of Cr, more than 8 weight % 8 to 16 weight % of Mo; and the remainder of Co and inevitable impurities; the wire having a diameter of 200 micrometers or less and a degree of roundness (minor diameter/major diameter) of lateral cross section is 0.6 or more, and wherein an internal structure is substantially composed of either gamma phase (Co base solid solution of face-centered cubic system) or epsilon phase (Co base solid solution of hexagonal close-packed system) only or both of them only.

Claim 16 (Original) The Co-Cr-Mo alloy fine wire of claim 15, wherein the roundness of lateral cross section is 0.7 or more.

Claim 17 (Original) A manufacturing method for Co-Cr-Mo alloy fine wire, the method comprising the step of:

injecting a molten alloy comprising 26 to 31 weight % of Cr, 8 to 16 weight % of Mo, and the remainder of Co and inevitable impurities into a coolant layer formed along the inner circumference of a rotating cylindrical drum to obtain a fine wire of diameter of 200 micrometers or less, and roundness (minor diameter/major diameter) of lateral cross

TECH/400118.1

Appln. No. 10/821,170
Reply to Office action of September 19, 2005
Response dated February 21, 2006

section of 0.6 or more, with an internal structure substantially composed of either gamma phase (Co base solid solution of face-centered cubic system) or epsilon phase (Co base solid solution of hexagonal close-packed system) only, or both of them only.

Claim 18 (Original) A manufacturing method for Co-Cr-Mo alloy fine wire, the method comprising the steps of:

injecting a molten alloy comprising 26 to 31 weight % of Cr, 3 to 16 weight % of Mo, and the remainder of Co and inevitable impurities from a nozzle of 200 micrometers or less in diameter; and

cooling and solidifying the injection jet in cooling gas to obtain a fine wire of diameter of 200 micrometers or less, and roundness (minor diameter/major diameter) of lateral cross section of 0.7 or more, with the internal structure substantially composed of either gamma phase (Co base solid solution of face-centered cubic system) or epsilon phase (Co base solid solution of hexagonal close-packed system) only, or both of them only.

Claim 19 (Original) A manufacturing method for Co-Cr-Mo alloy fine wire, the method comprising the steps of:

injecting downward a molten alloy comprising 26 to 31 weight % of Cr, 8 to 16 weight % of Mo, and the remainder of Co and inevitable impurities in falling state by a nozzle of 200 micrometers or less in diameter to form a molten alloy jet;

disposing a tube collecting gas so as to surround the falling part of the molten alloy jet;

feeding a cooling gas for solidifying the molten alloy jet into the tube collecting gas by a cooling gas feed means; and

discharging a fine wire obtained by solidification of the molten alloy jet to outside from the tube collecting gas by a discharge means;

thereby obtaining a fine wire of diameter of 200 micrometers or less, and roundness (minor diameter/major diameter) of lateral cross section of 0.7 or more, with the internal structure substantially composed of either gamma phase (Co base solid

TECH/400118.1

Appln. No. 10/821,170

Reply to Office action of September 19, 2005

Response dated February 21, 2006

solution of face-centered cubic system) or epsilon phase (Co base solid solution of hexagonal close-packed system) only, or both of them only.

Claim 20 (Original) The manufacturing method for Co-Cr-Mo alloy fine wire of claim 18, wherein the cooling gas is a gas containing oxygen.

Claim 21 (Original) The manufacturing method for Co-Cr-Mo alloy fine wire of claim 19, wherein the cooling gas is composed of a first gas component comprising inert gas introduced into the tube collecting gas at a first position closer to the nozzle in the falling direction of the molten alloy jet, a second gas component comprising oxidizing gas introduced into the tube collecting gas at a second position at lower side of the first position, and a third gas component of higher cooling capacity than the first and second gas components introduced into the tube collecting gas at a third position at lower side of the second position.

Claim 22 (Original) The manufacturing method for Co-Cr-Mo alloy fine wire of claim 21, wherein the first gas component is argon or helium, and the second gas component is oxygen or carbon dioxide.

Claim 23 (Original) A planar body formed by weaving, knitting or nonwoven processing of the Co-Cr-Mo alloy fine wire of claim 15.

Claim 24 (Original) A tubular body formed by weaving, knitting or nonwoven processing of the Co-Cr-Mo alloy fine wire of claim 15.

Claim 25 (Original) A stranded wire formed by processing of the Co-Cr-Mo alloy fine wire of claim 15.

Claim 26 (Original) A cable formed by processing of the Co-Cr-Mo alloy fine wire of claim 15.

TECH/400118.1